

Typical Data

		Units
Canadian Standard Freeness	450	mL
ISO Brightness	30	%
Ash	<2.0	%

Typical Unrefined Hand Sheet Properties

		Units
Tensile Index	35	N·m/g
Burst Index	3.8	kPa·m ² /g
Tear Index	7	mN·m ² /g
Bulk	1.75	cm ³ /g
Stretch	1.8	%

Typical Fiber Properties

		Units
Dirt	<0.25	%
Shives	<0.25	%
Fiber Length, LWAFL	0.9	mm
Fines, <0.2 mm, length weighted	5	%